

Propiedad Química y Mecánica – ASTM A778																		
Material	Composición Química													Propiedad Mecánica				
ASTM A 778/ 01 TP. 304L	TOL	C%	Mn%	P%	S%	Si%	Cu%	Ni%	Cr%	Mo%	Fe%	Sn%	A%	LR MPa/KSI	LF MPa/KSI	AL%	EX%	DUR HRB
	MAX.	0.030	2.00	0.045	0.030	1.00		13.00	20.00									
	MIN.							8.0	18.00					485/70				
ASTM A 778/ 01 TP. 316L	TOL	C%	Mn%	P%	S%	Si%	Cu%	Ni%	Cr%	Mo%	Fe%	Sn%	A%	LR MPa	LF MPa	AL%	EX%	DUR HRB
	MAX.	0.030	2.00	0.045	0.030	1.00		14.00	18.00	3.00								
	MIN.							10.00	16.00	2.00				485/70				